RECEIVED CENTRAL FAX CENTER

MAR 1 2 2007

IN THE CLAIMS:

- (Original) A polymerization process comprising contacting one or more monomer(s), one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor.
- 2. (Original) The process of claim 1, wherein one or more hydrofluorocarbon(s) is represented by the formula: $C_xH_yF_z$ wherein x is an integer from 1 to 40 and y and z are integers of one or more.
- 3. (Original) The process of claim 2, wherein x is from 1 to 10.
- 4. (Original) The process of claim 2, wherein x is from 1 to 6.
- 5. (Original) The process of claim 2, wherein x is from 1 to 3.
- (Original) The process of claim 1, wherein the one or more hydrofluorocarbon(s) is 6. independently selected from the group consisting of fluoromethane; difluoromethane; 1,1,1-1.2-difluoroethane; 1,1-difluoroethane; fluoroethane; trifluoromethane; 1,1,1,2-tetrafluoroethane; 1,1,2,2-1,1,2-trifluoroethane; trifluoroethane; tetrafluoroethane; 1,1,1,2,2-pentafluoroethane; 1-fluoropropane; 2-fluoropropane; 1,1difluoropropane; 1,2-difluoropropane; 1,3-difluoropropane; 2,2-difluoropropane; 1,1,3-trifluoropropane; 1,2,2-1,1,2-trifluoropropane; 1,1,1-trifluoropropane; 1,1,1,2-tetrafluoropropane; 1,1,1,3-1,2,3-trifluoropropane; trifluoropropane; tetrafluoropropane; 1,1,2,2-tetrafluoropropane; 1,1,2,3-tetrafluoropropane; 1,1,3,3-1,1,1,2,2-pentafluoropropane; 1,2,2,3-tetrafluoropropane; tetrafluoropropane; 1,1,2,2,3-1,1,1,3,3-pentafluoropropane; 1,1,1,2,3-pentafluoropropane; 1,1,2,3,3-pentafluoropropane; 1,1,1,2,2,3-hexafluoropropane; pentafluoropropane; 1,1,1,3,3,3-hexafluoropropane; 1,1,1,2,2,3,3-1,1,1,2,3,3-hexafluoropropane; 1-fluorobutane; 2-1,1,1,2,3,3,3-heptafluoropropane; heptafluoropropane; fluorobutane; 1,1-difluorobutane; 1,2-difluorobutane; 1,3-difluorobutane; difluorobutane; 2,2-difluorobutane; 2,3-difluorobutane; 1,1,1-trifluorobutane; 1,1,2trifluorobutane; 1,1,3-trifluorobutane; 1,1,4-trifluorobutane; 1,2,2-trifluorobutane; 1,1,1,2-2,2,3-trifluorobutane; 1,3,3-trifluorobutane; 1,2,3-trifluorobutane; 1,1,1,4-tetrafluorobutane; 1,1,2,2-1,1,1,3-tetrafluorobutane; tetrafluorobutane; 1,1,2,4-tetrafluorobutane; 1,1,3,3-1,1,2,3-tetrafluorobutane; tetrafluorobutane;

I:\Dpc\LAW\Prosecution\EMCC Prosecution\2003\2003\B133\US\2003B133-US-2007Mar12-Respon Non-Final Amdt.doc

> 1,1,4,4-tetrafluorobutane; 1,2,2,3-1,1,3,4-tetrafluorobutane; tetrafluorobutane; 1,2,3,3-tetrafluorobutane; 1,2,3,4-1,2,2,4-tetrafluorobutane; tetrafluorobutane; tetrafluorobutane; 2,2,3,3-tetrafluorobutane; 1,1,1,2,2-pentafluorobutane; 1,1,1,2,3-1,1,1,3,3-pentafluorobutane; 1,1,1,2,4-pentafluorobutane; pentafluorobutane; 1,1,2,2,3-1,1,1,4,4-pentafluorobutane; 1,1,1,3,4-pentafluorobutane; 1,1,2,3,3-pentafluorobutane; 1,1,2,2,4-pentafluorobutane; pentafluorobutane; 1,2,2,3,3-1,1,3,3,4-pentafluorobutane; 1,1,2,4,4-pentafluorobutane; 1,1,1,2,2,3-hexafluorobutane; 1,2,2,3,4-pentafluorobutane; pentafluorobutane; 1,1,1,2,3,4 1,1,1,2,3,3-hexafluorobutane, 1,1,1,2,2,4-hexafluorobutane; 1,1,1,3,3,4-hexafluorobutane; 1,1,1,2,4,4-hexafluorobutane; hexafluorobutane; 1,1,1,4,4,4-hexafluorobutane; 1,1,2,2,3,3-1,1,1,3,4,4-hexafluorobutane; 1,1,2,2,4,4-hexafluorobutane; 1,1,2,2,3,4-hexafluorobutane; hexafluorobutane; 1,2,2,3,3,4-1,1,2,3,4,4-hexafluorobutane; 1,1,2,3,3,4-hexafluorobutane; hexafluorobutane; 1,1,1,2,2,3,3-heptafluorobutane; 1,1,1,2,2,4,4-heptafluorobutane; 1,1,1,2,3,4,4-1,1,1,2,3,3,4-heptafluorobutane; 1,1,1,2,2,3,4-heptafluorobutane; heptafluorobutane; 1,1,1,2,4,4,4-heptafluorobutane; 1,1,1,3,3,4,4-heptafluorobutane; 1,1,1,2,2,3,3,4-octafluorobutane; 1,1,1,2,2,3,4,4-octafluorobutane; 1,1,1,2,3,3,4,4octafluorobutane; 1,1,1,2,2,4,4,4-octafluorobutane; 1,1,1,2,3,4,4,4-octafluorobutane; 1,1,1,2,2,3,3,4,4-nonafluorobutane; 1,1,1,2,2,3,4,4,4-nonafluorobutane; 1-fluoro-2methylpropane; 1,1-difluoro-2-methylpropane; 1,3-difluoro-2-methylpropane; 1,1,1-1,3-difluoro-2-1,1,3-trifluoro-2-methylpropane; trifluoro-2-methylpropane; (fluoromethyl)propane; 1,1,1,3-tetrafluoro-2-methylpropane; 1,1,3,3-tetrafluoro-2-1,1,1,3,3-pentafluoro-2-1,1,3-trifluoro-2-(fluoromethyl)propane; methylpropane; 1,1,3,3-tetrafluoro-2-(fluoromethyl)propane; 1,1,1,3-tetrafluoro-2methylpropane; 1,2-1,1-difluorocyclobutane; fluorocyclobutane; (fluoromethyl)propane; 1,1,3-1,1,2-trifluorocyclobutane; 1,3-difluorocyclobutane; difluorocyclobutane; 1,1,2,2-tetrafluorocyclobutane; 1,2,3-trifluorocyclobutane; trifluorocyclobutane; 1,1,2,2,3-pentafluorocyclobutane; 1,1,2,3,3-1,1,3,3-tctrafluorocyclobutane; 1,1,2,2,3,3-hexafluorocyclobutane; 1,1,2,2,3,4pentafluorocyclobutane; 1,1,2,2,3,3,4-1,1,2,3,3,4-hexafluorocyclobutane; hexafluorocyclobutane; heptafluorocyclobutane; vinyl fluoride; 1,1-difluoroethene; 1,2-difluoroethene; 1,1,2trifluoroethene; 1-fluoropropene, 1,1-difluoropropene; 1,2-difluoropropene; 1,3-

> difluoropropene; 2,3-difluoropropene; 3,3-difluoropropene; 1,1,2-trifluoropropene; 2,3,3-1,3,3-trifluoropropene; 1,2,3-trifluoropropene; 1,1,3-trifluoropropene; trifluoropropene; 3,3,3-trifluoropropene; 1-fluoro-1-butene; 2-fluoro-1-butene; 3fluoro-1-butene; 4-fluoro-1-butene; 1,1-difluoro-1-butene; 1,2-difluoro-1-butene; 1,3difluoropropene; 1,4-difluoro-1-butene; 2,3-difluoro-1-butene; 2,4-difluoro-1-butene; 3,3-difluoro-1-butene; 3,4-difluoro-1-butene; 4,4-difluoro-1-butene; 1,1,2-trifluoro-1butene; 1,1,3-trifluoro-1-butene; 1,1,4-trifluoro-1-butene; 1,2,3-trifluoro-1-butene; 1,2,4-trifluoro-1-butene; 1,3,4-trifluoro-1-butene; 1,4,4trifluoro-1-butene; 2,3,3-trifluoro-1-butene; 2,3,4-trifluoro-1-butene; 2,4,4-trifluoro-1butene; 3,3,4-trifluoro-1-butene; 3,4,4-trifluoro-1-butene; 4,4,4-trifluoro-1-butene; 1,1,3,3-tetrafluoro-1-1,1,2,4-tetrafluoro-1-butene; 1,1,2,3-tetrafluoro-1-butene; butene; 1,1,3,4-tetrafluoro-1-butene; 1,1,4,4-tetrafluoro-1-butene; 1,2,3,3-tetrafluoro-1,2,4,4-tetrafluoro-1-butene; 1,3,3,4 1,2,3,4-tetrafluoro-1-butene; 1-butene; 1,4,4,4-tetrafluoro-1-butene; 1,3,4,4-tetrafluoro-1-butene: tetrafluoro-1-butene; 2,4,4,4-tetrafluoro-1-2,3,4,4-tetrafluoro-1-butene; 2,3,3,4-tetrafluoro-1-butene; 1,1,2,3,3-3,4,4,4-tetrafluoro-1-butene; 3,3,4,4-tetrafluoro-1-butene; butene; pentafluoro-1-butene; 1,1,2,3,4-pentafluoro-1-butene; 1,1,2,4,4-pentafluoro-1-butene; 1,1,3,3,4-pentafluoro-1-butene; 1,1,3,4,4-pentafluoro-1-butene; 1,1,4,4,4-pentafluoro-1-butene; 1,2,3,3,4-pentafluoro-1-butene; 1,2,3,4,4-pentafluoro-1-butene; 1,2,4,4,4pentafluoro-1-butene; 2,3,3,4,4-pentafluoro-1-butene; 2,3,4,4,4-pentafluoro-1-butene; 1,1,2,3,3,4-hexafluoro-1-butene; 3,3,4,4,4-pentafluoro-1-butene; 1,2,3,3,4,4-hexafluoro-1-1,1,2,4,4,4-hexafluoro-1-butene; hexafluoro-1-butene; 2,3,3,4,4,4-hexafluoro-1-butene; 1,2,3,4,4,4-hexafluoro-1-butene; butene; 1,1,2,3,3,4,4-heptafluoro-1-butene; 1,1,2,3,4,4,4-heptafluoro-1-butene; 1,1,3,3,4,4,4heptafluoro-1-butene; 1,2,3,3,4,4,4-heptafluoro-1-butene; 1-fluoro-2-butene; 2-fluoro-2-butene; 1,1-difluoro-2-butene; 1,2-difluoro-2-butene; 1,3-difluoro-2-butene; 1,4difluoro-2-butene; 2,3-difluro-2-butene; 1,1,1-trifluoro-2-butene; 1,1,2-trifluoro-2butene; 1,1,3-trifluoro-2-butene; 1,1,4-trifluoro-2-butene; 1,2,3-trifluoro-2-butene; 1,2,4-trifluoro-2-butene; 1,1,1,2-tetrafluoro-2-butene; 1,1,1,3-tetrafluoro-2-butene; 1,1,2,4-tetrafluoro-2-1,1,2,3-tetrafluoro-2-butene; 1,1,1,4-tetrafluoro-2-butene; 1,2,3,4-tetrafluoro-2-butene; 1,1,1,2,3-pentafluoro-2-butene; butene; pentafluoro-2-butene; 1,1,1,3,4-pentafluoro-2-butene; 1,1,1,4,4-pentafluoro-2-butene;

- 1,1,2,3,4-pentafluoro-2-butene; 1,1,2,4,4-pentafluoro-2-butene; 1,1,1,2,3,4-hexafluoro-2-butene; 1,1,1,2,4,4-hexafluoro-2-butene; 1,1,1,4,4,4-hexafluoro-2-butene; 1,1,2,3,4,4-hexafluoro-2-butene; 1,1,2,3,4,4-hexafluoro-2-butene; 1,1,2,3,4,4-hexafluoro-2-butene; 1,1,1,2,3,4,4-heptafluoro-2-butene; and mixtures thereof.
- 7. (Original) The process of claim 1, wherein the one or more hydrofluorocarbon(s) is independently selected from the group consisting of fluoromethane, difluoromethane, trifluoromethane, 1,1-difluoroethane, 1,1,1-trifluoroethane, 1,1,1,2-tetrafluoroethane, and mixtures thereof.
- (Previously presented) The process of claim 1, wherein the diluent comprises from 15
 to 100 volume % HFC based upon the total volume of the diluent.
- (Original) The process of claim 8, wherein the diluent comprises from 20 to 100 volume % HFC based upon the total volume of the diluent.
- 10. (Original) The process of claim 9, wherein the diluent comprises from 25 to 100 volume % HFC based upon the total volume of the diluent.
- 11. (Previously presented) The process of claim 1, wherein the diluent further comprises a hydrocarbon, a non-reactive olefin, and/or an inert gas.
- 12. (Previously presented) The process of claim 1, wherein the diluent further comprises-a halogenated hydrocarbon other than an HFC.
- 13. (Previously presented) The process of claim 1, wherein the diluent further comprises methyl chloride.
- 14. (Previously presented) The process of claim 1, wherein the one or more Lewis acid(s) is represented by the formula MX₄;
 - wherein M is a Group 4, 5, or 14 metal; and each X is a halogen.
- 15. (Previously presented) The process of claim 1, wherein the one or more Lewis acid(s) is represented by the formula MR_nX_{4-n}:

 wherein M is Group 4, 5, or 14 metal;

each R is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals; n is an integer from 0 to 4; and each X is a halogen.

(Previously presented) The process of claim 1, wherein the one or more Lewis acid(s) is represented by the formula M(RO)_nR'_mX_{4-(m+n)};

wherein M is Group 4, 5, or 14 metal;

each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4, wherein the sum of n and m is not more than 4; and each X is a halogen.

17. (Previously presented) The process of claim 1, wherein the one or more Lewis acid(s) is represented by the formula M(RC=OO)_nR'_mX_{4-(m+n)};

wherein M is Group 4, 5, or 14 metal;

each RC=OO is a monovalent C₂ to C₃₀ hydrocarbacyl radical independently selected from the group consisting of an alkacyloxy, arylacyloxy, arylacyloxy, alkylarylacyloxy radicals;

each R' is a monovalent C₁ to C₁₂ hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4, wherein the sum of n and m is not more than 4; and each X is a halogen.

18. (Previously presented) The process of claim 1, wherein the one or more Lewis acid(s) is represented by the formula MOX₃;

wherein M is a Group 5 metal; and each X is a halogen.

19. (Previously presented) The process of claim 1, wherein the one or more Lewis acid(s) is represented by the formula MX₃;

wherein M is a Group 13 metal; and

each X is a halogen.

20. (Previously presented) The process of claim 1, wherein the one or more Lewis acid(s) is represented by the formula MR_nX_{3-n};

wherein M is a Group 13 metal;

each R is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 1 to 3; and

each X is a halogen.

21. (Previously presented) The process of claim 1, wherein the one or more Lewis acid(s) is represented by the formula M(RO)₀R'_mX_{3-(m+1)};

wherein M is a Group 13 metal;

each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 3;

m is an integer from 0 to 3, wherein the sum of n and m is from 1 to 3; and each X is a halogen.

22. (Previously presented) The process of claim 1, wherein the one or more Lewis acid(s) is represented by the formula M(RC=OO)_nR'_mX_{3-(m+n)};

wherein M is a Group 13 metal;

each RC=OO is a monovalent hydrocarbacyl radical independently selected from the group independently selected from the C₂ to C₃₀ group consisting of an alkacyloxy, arylacyloxy, arylacyloxy, alkylarylacyloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 3;

m is a integer from 0 to 3, wherein the sum of n and m is from 1 to 3; and each X is a halogen.

23. (Previously presented) A polymerization process comprising contacting one or more isoolefins, one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor, wherein the one or more Lewis acid(s) is represented by the formula MXy,

wherein M is a Group 15 metal;

each X is a halogen; and

y is 3, 4 or 5.

24. (Previously presented) A polymerization process comprising contacting one or more isoolefins, one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor, wherein the one or more Lewis acid(s) is represented by the formula:

MR_nX_{y-n};

wherein M is a Group 15 metal;

each R is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

y is 3, 4 or 5, wherein n is less than y; wherein the sum of n and m is less than y each X is a halogen.

25. (Previously presented) A polymerization process comprising contacting one or more isoolefins, one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor, wherein the one or more Lewis acid(s) is represented by the formula M(RO)_nR'_mX_{y-(m+n)}:

wherein M is a Group 15 metal,

each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4;

y is 3, 4 or 5, wherein the sum of n and m is less than y; and each X is a halogen.

26. (Previously presented) A polymerization process comprising contacting one or more isoolefins, one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor, wherein the one or more Lewis acid(s) is represented by the formula M(RC=OO)_nR'_mX_{y-(m+n)};

wherein M is a Group 15 metal;

each RC=OO is a monovalent C₂ to C₃₀ hydrocarbacyloxy radical independently selected from the group consisting of an alkacyloxy, arylacyloxy, arylacyloxy, arylacyloxy, alkylarylacyloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4;

y is 3, 4 or 5, wherein the sum of n and m is less than y; and each X is a halogen.

- (Previously presented) The process of claim 1, wherein the one or more Lewis acid(s) 27. is independently selected from the group consisting of titanium tetrachloride, titanium tetrabromide, vanadium tetrachloride, tin tetrachloride, zirconium tetrachloride, titanium bromide trichloride, titanium dibromide dichloride, vanadium bromide trichloride, tin chloride trifluoride, benzyltitanium trichloride, dibenzyltitanium dibromide, dibenzylzirconium trichloride, benzylzirconium dichloride, methyltitanium trichloride, dimethyltitanium difluoride, dimethyltin dichloride, n-butoxytitanium methoxytitanium trichloride, trichloride, phenylvanadium phenoxytitanium tribromide, dichloride, di(isopropoxy)titanium trichloride. phenylmethoxyzirconium trifluoride, methyl methoxytitanium dichloride, methyl methoxytin dichloride, benzyl isopropoxyvanadium dichloride, acetoxytitanium benzoyloxytitanium trifluoride, tribromide, benzoylzirconium trichloride, benzyl methyl acetoxytitanium dichloride, trichloride, isopropoyloxytin benzoyloxyvanadium chloride, vanadium oxytrichloride, aluminum trichloride, boron trifluoride, gallium trichloride, indium trifluoride, ethylaluminum dichloride, methylaluminum dichloride, benzylaluminum dichloride, isobutylgallium dichloride, ethylaluminum dimethylaluminum chloride, chloride, diethylaluminum trimethylaluminum, sesquichloride methylaluminum sesquichloride, triethylaluminum, methoxyaluminum dichloride, ethoxyaluminum dichloride, 2,6-ditert-butylphenoxyaluminum dichloride, methoxy methylaluminum chloride, 2,6-ditert-butylphenoxy methylaluminum chloride, isopropoxygallium dichloride, phenoxy benzoyloxyaluminum acetoxyaluminum dichloride, fluoride, methylindium dibromide, benzoyloxygallium difluoride, methyl acetoxyaluminum chloride, isopropoyloxyindium trichloride, antimony hexachloride, antimony hexafluoride, arsenic pentafluoride, antimony chloride pentafluoride, arsenic trifluoride, bismuth tetraphenylantimony chloride, tetrachloride, fluoride arsenic trichloride tetrachloromethoxyantimony, dichloride, triphenylantimony chlorodimethoxyarsine, dichloromethoxyarsine, dimethoxytrichloroantimony, difluoromethoxyarsine, acetatotetrachloroantimony, (benzoato) tetrachloroantimony, and bismuth acetate chloride.
 - 28. (Previously presented) The process of claim 1, wherein the one or more Lewis acid(s) is independently selected from the group consisting of aluminum trichloride,

aluminum tribromide, ethylaluminum dichloride, ethylaluminum sesquichloride, diethylaluminum chloride, methylaluminum dichloride, methylaluminum sesquichloride, dimethylaluminum chloride, boron trifluoride, and titanium tetrachloride.

- 29. (Previously presented) The process of claim 1, wherein the one or more initiator(s) comprise a hydrogen halide, a carboxylic acid, a carboxylic acid halide, a sulfonic acid, an alcohol, a phenol, a polymeric halide, a tertiary alkyl halide, a tertiary aralkyl halide, a tertiary alkyl ester, a tertiary aralkyl ester, a tertiary aralkyl ether, an alkyl halide, an aryl halide, an alkylaryl halide or an arylalkylacid halide.
- 30. (Previously presented) A polymerization process comprising contacting one or more isoolefins, one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor, wherein the one or more initiator(s) is independently selected from the group consisting of HCl, H₂O, methanol, (CH₃)₃CCl, C₆H₅C(CH₃)₂Cl, (2-Chloro-2,4,4-trimethylpentane) and 2-chloro-2-methylpropane.
- (Previously presented) A polymerization process comprising contacting one or more 31. isoolefins, one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor, wherein the one or more initiator(s) is independently selected from the group consisting of hydrogen chloride, hydrogen bromide, hydrogen iodide, acetic acid, propanoic acid, butanoic acid; cinnamic acid, benzoic acid, 1-chloroacetic acid, dichloroacetic acid, trichloroacetic acid, trifluoroacetic acid, p-chlorobenzoic acid, p-fluorobenzoic acid, acetyl chloride, acetyl bromide, cinnamyl chloride, benzoyl chloride, benzoyl bromide, trichloroacetylchloride, trifluoroacetylchloride, p-fluorobenzoylchloride, methanesulfonic acid, trifluoromethanesulfonic acid, trichloromethanesulfonic acid, p-toluenesulfonic acid, methanesulfonyl chloride, methanesulfonyl bromide, chloride, trifluoromethanesulfonyl trichloromethanesulfonyl chloride, toluenesulfonyl chloride, methanol, ethanol, propanol, 2-propanol, 2-methylpropan-2ol, cyclohexanol, benzyl alcohol, phenol, 2-methylphenol, 2,6-dimethylphenol, p-

- chlorophenol, p-fluorophenol, 2,3,4,5,6-pentafluorophenol, and 2-hydroxynaphthalene.
- (Previously presented) A polymerization process comprising contacting one or more 32. isoolefins, one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor, wherein the one or more initiator(s) is independently selected from the group consisting of 2-chloro-2,4,4-trimethylpentane; 2-bromo-2,4,4-trimethylpentane; 2-chloro-2-methylpropane; 2-chloro-2,4,4,6,6-pentamethylheptane; 2-bromo-2-bromo-2-methylpropane; 2,4,4,6,6-pentamethylheptane; 1-chloro-1-methylethylbenzene; 1-chloroadamantane; 1-chloroethylbenzene; 1, 4-bis(1-chloro-1-methylethyl) benzene; 5-tert-butyl-1,3-2-acetoxy-2,4,4-trimethylpentane; bis(1-chloro-1-methylethyl) benzene; benzoyloxy-2,4,4-trimethylpentane; 2-acetoxy-2-methylpropane; 2-benzoyloxy-2-2-benzoyl-2,4,4,6,6methylpropane; 2-acetoxy-2,4,4,6,6-pentamethylheptane; pentamethylheptane; 1-acetoxy-1-methylethylbenzene; 1-aceotxyadamantane; 1benzoyloxyethylbenzene; 1,4-bis(1-acetoxy-1-methylethyl) benzene; 5-tert-butyl-1,3-2-methoxy-2,4,4-trimethylpentane; bis(1-acetoxy-1-methylethyl) benzene; isopropoxy-2,4,4-trimethylpentane; 2-methoxy-2-methylpropane; 2-benzyloxy-2methylpropane; 2-methoxy-2,4,4,6,6-pentamethylheptane; 2-isopropoxy-2,4,4,6,6pentamethylheptane; 1-methoxy-1-methylethylbenzene; 1-methoxyadamantane; 1methoxyethylbenzene; 1,4-bis(1-methoxy-1-methylethyl) benzene; 5-tert-butyl-1,3-1,3,5-tris(1-chloro-1-methylethyl) bis(1-methoxy-1-methylethyl) benzene, and benzene.
 - 33. (Previously presented) A polymerization process comprising contacting one or more isoolefins, one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor, wherein the one or more initiator(s) further comprise a weakly-coordinating anion.
 - 34. (Previously presented) The process of claim 1, wherein the process is substantially absent of water.
 - 35. (Previously presented) A polymerization process comprising contacting one or more isoolefins, one or more Lewis acid(s), one or more initiator(s), and a diluent

- comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor, wherein the one or more initiator(s) comprise greater than 30 ppm water (based upon weight).
- 36. (Previously presented) The process of claim 1, wherein the one or more monomer(s) is independently selected from the group consisting of olefins, alpha-olefins, disubstituted olefins, isoolefins, conjugated dienes, non-conjugated dienes, styrenics, substituted styrenics, and vinyl ethers.
- 37. (Previously presented) The process of claim 1, wherein the one or more monomer(s) is independently selected from the group consisting of styrene, para-alkylstyrene, para-methylstyrene, alpha-methyl styrene, divinylbenzene, diisopropenylbenzene, isobutylene, 2-methyl-1-butene, 3-methyl-1-butene, 2-methyl-2-pentene, isoprene, butadiene, 2,3-dimethyl-1,3-butadiene, β-pinene, myrcene, 6,6-dimethyl-fulvene, hexadiene, cyclopentadiene, methyl cyclopentadiene, piperylene, methyl vinyl ether, ethyl vinyl ether, and isobutyl vinyl ether.
- 38. (Previously presented) The process of claim 1, wherein the reactor is independently selected from the group consisting of a continuous flow stirred tank reactor, a plug flow reactor, a moving belt or drum reactor, a jet or nozzle reactor, a tubular reactor, a batch reactor, and an autorefrigerated boiling-pool reactor.
- 39. (Previously presented) The polymerization process of claim 1, wherein the diluent has a dielectric constant greater than 10 at -85°C.
- 40. (Original) The process of claim 39, wherein the dielectric constant is greater than 20 at -85°C.
- 41. (Original) The process of claim 40, wherein the dielectric constant is greater than 25 at -85°C.
- 42. (Previously presented) A polymerization process comprising contacting one or more isoolefins, one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor, wherein the diluent has a dielectric constant greater than 40 at -85°C.
- 43. (Previously presented) The polymerization process of claim 1, wherein polymerization process forms a polymer having a diluent mass uptake of less than 4 wt%.

- 44. (Original) The process of claim 43, wherein the polymer has a diluent mass uptake of less than 3 wt%.
- 45. (Original) The process of claim 44, wherein the polymer has a diluent mass uptake of less than 2 wt%.
- 46. (Original) The process of claim 45, wherein the polymer has a diluent mass uptake of less than 1 wt%.
- 47. (Original) The process of claim 46, wherein the polymer has a diluent mass uptake of less than 0.5 wt%.
- 48. (Previously presented) The polymerization process of claim 1, the diluent comprising methyl chloride and one or more hydrofluorocarbon(s) independently selected from the group consisting of difluoromethane, 1,1-difluoroethane, and 1,1,1,2-tetrafluoroethane.
- 49. (Original) The process of claim 48 wherein the diluent further comprises a non-reactive olefin, one or more other hydrocarbons, and/or an inert gas.
- 50. (Previously presented) The polymerization process of claim 1, the process comprising the steps of:
 - reacting the one or more monomer(s) in the presence of one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's); and
 - withdrawing the polymer from the reactor.
- 51. (Previously presented) The polymerization process of claim 1, the process comprising the steps of:
 - (a) introducing one or more monomer(s) into a reactor;
 - (b) adding one or more Lewis acid(s) and one or more initiator(s);
 - (c) introducing a diluent comprising one or more hydrofluorocarbon(s) (HFC's); and
 - (d) withdrawing a polymer from the reactor.

- 52. (Previously presented) The polymerization process of claim 1 in which particles of polymer are produced_using a catalyst system and a diluent comprising one or more hydrofluorocarbon(s) (HFC's).
- 53. (Previously presented) The polymerization process of claim 1 in which particles of polymer are produced_in a slurry using a carbocationic catalyst system and a diluent comprising one or more hydrofluorocarbon(s) (HFC's).
- 54. (Previously presented) The polymerization process of claim 1 in which particles of polymer are produced using a catalyst system and a diluent, the diluent having a dielectric constant greater than 18.50 at -85°C.
- 55. (Original) The process of claim 54, wherein the dielectric constant is greater than 19.00 at -85°C.
- 56. (Original) The process of claim 55, wherein the dielectric constant is greater than 20.00 at -85°C.
- 57. (Original) The process of claim 56, wherein the dielectric constant is greater than 25.00 at -85°C.
- 58. (Original) The process of claim 57, wherein the dielectric constant is greater than 30.00 at -85°C.
- 59. (Original) The process of claim 58, wherein the dielectric constant is greater than 35.00 at -85°C.
- 60. (Previously presented) A polymerization process comprising contacting one or more isoolefins, one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor, in which particles of polymer are produced using a catalyst system and a diluent, the diluent having a dielectric constant greater than 40.00 at -85°C.
- 61. (Previously presented) The process of claim 1, wherein the diluent is independently selected from the group consisting of at least one of a hydrofluorocarbon or a blend of a hydrofluorocarbon and methyl chloride.
- 62. (Cancelled)
- 63. (Cancelled)

- 64. (Original) A polymerization medium suitable to polymerize one or more monomer(s) to form a polymer, the polymerization medium comprising one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's).
- 65. (Cancelled)
- 66. (Cancelled)
- 67. (Cancelled)
- 68. (Cancelled)
- 69. (Cancelled)
- 70. (Previously presented) The polymerization process of claim 1, wherein the diluent has a dielectric constant greater than 40 at -85°C.
- 71. (Previously presented) A polymerization process comprising contacting one or more monomers comprising isoolefin(s), one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor.
- 72. (Previously presented) The process of claim 71, wherein one or more hydrofluorocarbon(s) is represented by the formula: $C_xH_yF_z$ wherein x is an integer from 1 to 40 and y and z are integers of one or more.
- 73. (Previously presented) The process of claim 72, wherein x is from 1 to 10.
- 74. (Previously presented) The process of claim 72, wherein x is from 1 to 6.
- 75. (Previously presented) The process of claim 72, wherein x is from 1 to 3.
- (Previously presented) The process of claim 71, wherein the one or more 76. hydrofluorocarbon(s) is independently selected from the group consisting of fluoromethane; difluoromethane; trifluoromethane; fluoroethane; 1,1-difluoroethane; 1,1,2-trifluoroethane; 1,1,1,2-1,1,1-trifluoroethane; 1,2-difluoroethane; 1,1,1,2,2-pentafluoroethane; 1,1,2,2-tetrafluoroethane; tetrafluoroethane; fluoropropane; 2-fluoropropane; 1,1-difluoropropane; 1,2-difluoropropane; difluoropropane; 2,2-difluoropropane; 1,1,1-trifluoropropane; 1,1,2-trifluoropropane; 1,2,3-trifluoropropane; 1,1,1,2-1,2,2-trifluoropropane; 1,1,3-trifluoropropane;

> tetrafluoropropane; 1,1,1,3-tetrafluoropropane; 1,1,2,2-tetrafluoropropane; 1,1,2,3tetrafluoropropane; 1,1,3,3-tetrafluoropropane; 1,2,2,3-tetrafluoropropane; 1,1,1,2,2-1,1,1,3,3-pentafluoropropane; 1,1,1,2,3-pentafluoropropane; pentafluoropropane; 1,1,1,2,2,3-1,1,2,3,3-pentafluoropropane; 1,1,2,2,3-pentafluoropropane; hexafluoropropane; 1,1,1,2,3,3-hexafluoropropane; 1,1,1,3,3,3-hexafluoropropane; 1,1,1,2,2,3,3-heptafluoropropane; 1,1,1,2,3,3,3-heptafluoropropane; 1-fluorobutane; 2-fluorobutane; 1,1-difluorobutane; 1,2-difluorobutane; 1,3-difluorobutane; 1,4difluorobutane; 2,2-difluorobutane; 2,3-difluorobutane; 1,1,1-trifluorobutane; 1,1,2trifluorobutane; 1,1,3-trifluorobutane; 1,1,4-trifluorobutane; 1,2,2-trifluorobutane; 1,1,1,2-2,2,3-trifluorobutane; 1,3,3-trifluorobutane; 1,2,3-trifluorobutane; 1,1,4-tetrafluorobutane: 1,1,2,2-1,1,1,3-tetrafluorobutane; tetrafluorobutane; 1,1,2,4-tetrafluorobutane; 1,1,3,3-1,1,2,3-tetrafluorobutane; tetrafluorobutane; 1,1,4,4-tetrafluorobutane; 1,2,2,3-1,1,3,4-tetrafluorobutane; tetrafluorobutane; 1,2,3,4-1,2,3,3-tetrafluorobutane; 1,2,2,4-tetrafluorobutane; tetrafluorobutane; tetrafluorobutane; 2,2,3,3-tetrafluorobutane; 1,1,1,2,2-pentafluorobutane; 1,1,1,2,3-1,1,1,3,3-pentafluorobutane; 1,1,1,2,4-pentafluorobutane: pentafluorobutane; 1,1,2,2,3-1,1,1,4,4-pentafluorobutane; 1,1,1,3,4-pentafluorobutane; 1,1,2,3,3-pentafluorobutane; 1,1,2,2,4-pentafluorobutane; pentafluorobutane; 1,2,2,3,3-1,1,3,3,4-pentafluorobutane; 1,1,2,4,4-pentafluorobutane; 1,1,1,2,2,3-hexafluorobutane; 1,2,2,3,4-pentafluorobutane; pentafluorobutane; 1,1,1,2,3,4-1,1,1,2,3,3-hexafluorobutane, 1,1,1,2,2,4-hexafluorobutane; 1,1,1,3,3,4-hexafluorobutane; 1,1,1,2,4,4-hexafluorobutane; hexafluorobutane; 1,1,2,2,3,3-1,1,1,4,4,4-hexafluorobutane; 1,1,1,3,4,4-hexafluorobutane; 1,1,2,2,4,4-hexafluorobutane; 1,1,2,2,3,4-hexafluorobutane; hexafluorobutane; 1,2,2,3,3,4 1,1,2,3,4,4-hexafluorobutane; 1,1,2,3,3,4-hexafluorobutane; hexafluorobutane; 1,1,1,2,2,3,3-heptafluorobutane; 1,1,1,2,2,4,4-heptafluorobutane; 1,1,1,2,3,4,4-1,1,1,2,3,3,4-heptafluorobutane; 1,1,1,2,2,3,4-heptafluorobutane; heptafluorobutane; 1,1,1,2,4,4,4-heptafluorobutane; 1,1,1,3,3,4,4-heptafluorobutane; 1,1,1,2,2,3,3,4-octafluorobutane; 1,1,1,2,2,3,4,4-octafluorobutane; 1,1,1,2,3,3,4,4octafluorobutane; 1,1,1,2,2,4,4,4-octafluorobutane; 1,1,1,2,3,4,4,4-octafluorobutane; 1,1,1,2,2,3,3,4,4-nonafluorobutane; 1,1,1,2,2,3,4,4,4-nonafluorobutane; 1-fluoro-2methylpropane; 1,1-difluoro-2-methylpropane; 1,3-difluoro-2-methylpropane; 1,1,1-

> 1.3-difluoro-2-1,1,3-trifluoro-2-methylpropane; trifluoro-2-methylpropane; 1,1,3,3-tetrafluoro-2-methylpropane; 1,1,3,3-tetrafluoro-2-(fluoromethyl)propane; 1,1,1,3,3-pentafluoro-2-1,1,3-trifluoro-2-(fluoromethyl)propane; methylpropane; 1,1,3,3-tetrafluoro-2-(fluoromethyl)propane; 1,1,1,3-tetrafluoro-2methylpropane; 1,2-1,1-difluorocyclobutane; fluorocyclobutane; (fluoromethyl)propane; 1,3-difluorocyclobutane; 1,1,2-trifluorocyclobutane; 1.1.3difluorocyclobutane; 1,1,2,2-tetrafluorocyclobutane; 1,2,3-trifluorocyclobutane; trifluorocyclobutane; 1,1,2,3,3-1,1,2,2,3-pentafluorocyclobutane; 1,1,3,3-tetrafluorocyclobutane; 1,1,2,2,3,4-1,1,2,2,3,3-hexafluorocyclobutane; pentafluorocyclobutane; 1.1,2,2,3,3,4-1,1,2,3,3,4-hexafluorocyclobutane; hexafluorocyclobutane; heptafluorocyclobutane; vinyl fluoride; 1,1-difluoroethene; 1,2-difluoroethene; 1,1,2trifluoroethene; 1-fluoropropene, 1,1-difluoropropene; 1,2-difluoropropene; 1,3difluoropropene; 2,3-difluoropropene; 3,3-difluoropropene; 1,1,2-trifluoropropene; 2,3,3-1,3,3-trifluoropropene; 1,2,3-trifluoropropene; 1.1,3-trifluoropropene; trifluoropropene; 3,3,3-trifluoropropene; 1-fluoro-1-butene; 2-fluoro-1-butene; 3fluoro-1-butene; 4-fluoro-1-butene; 1,1-difluoro-1-butene; 1,2-difluoro-1-butene; 1,3difluoropropene; 1,4-difluoro-1-butene; 2,3-difluoro-1-butene; 2,4-difluoro-1-butene; 3,3-difluoro-1-butene; 3,4-difluoro-1-butene; 4,4-difluoro-1-butene; 1,1,2-trifluoro-1butene; 1,1,3-trifluoro-1-butene; 1,1,4-trifluoro-1-butene; 1,2,3-trifluoro-1-butene; 1,2,4-trifluoro-1-butene; 1,3,3-trifluoro-1-butene; 1,3,4-trifluoro-1-butene; 1,4,4trifluoro-1-butene; 2,3,3-trifluoro-1-butene; 2,3,4-trifluoro-1-butene; 2,4,4-trifluoro-1butene; 3,3,4-trifluoro-1-butene; 3,4,4-trifluoro-1-butene; 4,4,4-trifluoro-1-butene; 1,1,3,3-tetrafluoro-1-1,1,2,4-tetrafluoro-1-butene; 1,1,2,3-tetrafluoro-1-butenc; butene; 1,1,3,4-tetrafluoro-1-butene; 1,1,4,4-tetrafluoro-1-butene; 1,2,3,3-tetrafluoro-1.3.3.4-1,2,4,4-tetrafluoro-1-butene; 1,2,3,4-tetrafluoro-1-butene; I-butene; 1,4,4,4-tetrafluoro-1-butene; 1,3,4,4-tetrafluoro-1-butene; tetrafluoro-1-butene; 2,4,4,4-tetrafluoro-l-2,3,4,4-tetrafluoro-1-butene; 2,3,3,4-tetrafluoro-1-butene; 3,4,4,4-tetrafluoro-1-butene; 3,3,4,4-tetrafluoro-1-butene; butene; pentafluoro-1-butene; 1,1,2,3,4-pentafluoro-1-butene; 1,1,2,4,4-pentafluoro-1-butene; 1,1,3,3,4-pentafluoro-1-butene; 1,1,3,4,4-pentafluoro-1-butene; 1,1,4,4,4-pentafluoro-1-butene; 1,2,3,3,4-pentafluoro-1-butene; 1,2,3,4,4-pentafluoro-1-butene; 1,2,4,4,4pentafluoro-1-butene; 2,3,3,4,4-pentafluoro-1-butene; 2,3,4,4,4-pentafluoro-1-butene;

- 1,1,2,3,3,4-hexafluoro-1-butene; 1,1,2,3,4,4-3,3,4,4,4-pentafluoro-1-butene; 1,2,3,3,4,4-hexafluoro-1-1,1,2,4,4,4-hexafluoro-1-butene; hexafluoro-1-butene; 2,3,3,4,4,4-hexafluoro-1-butene; 1,2,3,4,4,4-hexafluoro-1-butene; butene; 1,1,2,3,3,4,4-heptafluoro-1-butene; 1,1,2,3,4,4,4-heptafluoro-1-butene; 1,1,3,3,4,4,4heptafluoro-1-butene; 1,2,3,3,4,4,4-heptafluoro-1-butene; 1-fluoro-2-butene; 2-fluoro-2-butene; 1,1-difluoro-2-butene; 1,2-difluoro-2-butene; 1,3-difluoro-2-butene; 1,4difluoro-2-butene; 2,3-difluro-2-butene; 1,1,1-trifluoro-2-butene; 1,1,2-trifluoro-2butene; 1,1,3-trifluoro-2-butene; 1,1,4-trifluoro-2-butene; 1,2,3-trifluoro-2-butene; 1,2,4-trifluoro-2-butene; 1,1,1,2-tetrafluoro-2-butene; 1,1,1,3-tetrafluoro-2-butene; 1,1,2,4-tetrafluoro-2-1,1,2,3-tetrafluoro-2-butene; 1,1,1,4-tetrafluoro-2-butene; 1,1,1,2,3-pentafluoro-2-butene; 1,2,3,4-tetrafluoro-2-butene; butene; pentafluoro-2-butene; 1,1,1,3,4-pentafluoro-2-butene; 1,1,1,4,4-pentafluoro-2-butene; 1,1,2,4,4-pentafluoro-2-butene; 1,1,1,2,3,4-1,1,2,3,4-pentafluoro-2-butene; 1,1,1,3,4,4-hexafluoro-2-1,1,1,2,4,4-hexafluoro-2-butene; hexafluoro-2-butene; 1,1,2,3,4,4-hexafluoro-2-butene; 1,1,1,4,4,4-hexafluoro-2-butene; butene; 1,1,1,2,3,4,4-heptafluoro-2-butene; 1,1,1,2,4,4,4-heptafluoro-2-butene; and mixtures thereof.
- 77. (Previously presented) The process of claim 71, wherein the one or more hydrofluorocarbon(s) is independently selected from the group consisting of fluoromethane, difluoromethane, trifluoromethane, 1,1-difluoroethane, 1,1,1-trifluoroethane, 1,1,1,2-tetrafluoroethane, and mixtures thereof.
- 78. (Previously presented) The process of claim 71, wherein the diluent comprises from 15 to 100 volume % HFC based upon the total volume of the diluent.
- 79. (Previously presented) The process of claim 78, wherein the diluent comprises from 20 to 100 volume % HFC based upon the total volume of the diluent.
- 80. (Previously presented) The process of claim 79, wherein the diluent comprises from 25 to 100 volume % HFC based upon the total volume of the diluent.
- 81. (Previously presented) The process of claim 71, wherein the diluent further comprises a hydrocarbon, a non-reactive olefin, and/or an inert gas.

- 82. (Previously presented) The process of claim 71, wherein the diluent further comprises a halogenated hydrocarbon other than an HFC.
- 83. (Previously presented) The process of claim 71, wherein the diluent further comprises methyl chloride.
- 84. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula MX₄;

wherein M is a Group 4, 5, or 14 metal; and each X is a halogen.

85. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula MR_nX_{4-n};

wherein M is Group 4, 5, or 14 metal;

each R is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4; and

each X is a halogen.

86. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula M(RO)_nR'_mX_{4-(m+n)};

wherein M is Group 4, 5, or 14 metal;

each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4, wherein the sum of n and m is not more than 4; and each X is a halogen.

87. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula M(RC=OO)_nR'_mX_{4-{m+n}};

wherein M is Group 4, 5, or 14 metal;

each RC=OO is a monovalent C_2 to C_{30} hydrocarbacyl radical independently selected from the group consisting of an alkacyloxy, arylacyloxy, arylacyloxy, alkylarylacyloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4, wherein the sum of n and m is not more than 4; and each X is a halogen.

88. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula MOX₃;

wherein M is a Group 5 metal; and

each X is a halogen.

89. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula MX₃;

wherein M is a Group 13 metal; and

each X is a halogen.

90. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula MR_nX_{3-n};

wherein M is a Group 13 metal;

each R is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 1 to 3; and

each X is a halogen.

91. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula M(RO)_nR'_{in}X_{3-(m+n)};

wherein M is a Group 13 metal;

each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 3;

m is an integer from 0 to 3, wherein the sum of n and m is from 1 to 3; and each X is a halogen.

92. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula M(RC=OO)_nR'_mX_{3-(m+n)};

wherein M is a Group 13 metal;

each RC=OO is a monovalent hydrocarbacyl radical independently selected from the group independently selected from the C₂ to C₃₀ group consisting of an alkacyloxy, arylacyloxy, arylacyloxy, alkylarylacyloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 3;

m is a integer from 0 to 3, wherein the sum of n and m is from 1 to 3; and each X is a halogen.

93. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula MX_y,

wherein M is a Group 15 metal;

each X is a halogen; and

y is 3, 4 or 5.

94. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula:

MR_nX_{y-n;}

wherein M is a Group 15 metal;

1:\Bpc\LAW\Prosecution\EMCC Prosecution\2003\2003B133\US\2003B133-US-2007Mer12-Respon Non-Final Amdi.doc

each R is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

y is 3, 4 or 5, wherein n is less than y; wherein the sum of n and m is less than y each X is a halogen.

95. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula M(RO)_nR'_mX_{y-(m+n)};

wherein M is a Group 15 metal,

each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4;

y is 3, 4 or 5, wherein the sum of n and m is less than y; and

each X is a halogen.

96. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is represented by the formula M(RC=OO)₁R'_mX_{y-(m+1)};

wherein M is a Group 15 metal;

each RC=OO is a monovalent C₂ to C₃₀ hydrocarbacyloxy radical independently selected from the group consisting of an alkacyloxy, arylacyloxy, arylacyloxy, arylacyloxy, alkylarylacyloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4;

y is 3, 4 or 5, wherein the sum of n and m is less than y; and

each X is a halogen.

(Previously presented) The process of claim 71, wherein the one or more Lewis 97. acid(s) is independently selected from the group consisting of titanium tetrachloride, titanium tetrabromide, vanadium tetrachloride, tin tetrachloride, zirconium tetrachloride, titanium bromide trichloride, titanium dibromide dichloride, vanadium benzyltitanium trifluoride, chloride trichloride, tin bromide dibenzylzirconium trichloride, benzylzirconium dichloride, dibenzyltitanium dibromide, methyltitanium trichloride, dimethyltitanium difluoride, dimethyltin trichloride, methoxytitanium trichloride, phenylvanadium dichloride. butoxytitanium trichloride, di(isopropoxy)titanium dichloride, phenoxytitanium tribromide, phenylmethoxyzirconium trifluoride, methyl methoxytitanium dichloride, isopropoxyvanadium dichloride, benzyl dichloride, methoxytin methyl benzoylzirconium tribromide, benzoyloxytitanium acetoxytitanium trichloride, trifluoride, isopropoyloxytin trichloride, methyl acetoxytitanium dichloride, benzyl benzoyloxyvanadium chloride, vanadium oxytrichloride, aluminum trichloride, boron trifluoride, gallium trichloride, indium trifluoride, ethylaluminum dichloride, methylaluminum dichloride, benzylaluminum dichloride, isobutylgallium dichloride, ethylaluminum chloride. dimethylaluminum chloride. diethylaluminum trimethylaluminum, sesquichloride methylaluminum sesquichloride, triethylaluminum, methoxyaluminum dichloride, ethoxyaluminum dichloride, 2,6-ditert-butylphenoxyaluminum dichloride, methoxy methylaluminum chloride, 2,6-ditert-butylphenoxy methylaluminum chloride, isopropoxygallium dichloride, phenoxy benzoyloxyaluminum dichloride, acetoxyaluminum fluoride. methylindium dibromide, benzoyloxygallium difluoride, methyl acetoxyaluminum chloride, isopropoyloxyindium trichloride, antimony hexachloride, antimony hexafluoride, arsenic pentafluoride, antimony chloride pentafluoride, arsenic trifluoride, bismuth tetraphenylantimony chloride, fluoride tetrachloride. arsenic trichloride tetrachloromethoxyantimony, dichloride, triphenylantimony chlorodimethoxyarsine, dichloromethoxyarsine, dimethoxytrichloroantimony, difluoromethoxyarsine, acetatotetrachloroantimony, (benzoato) tetrachloroantimony, and bismuth acetate chloride.

- 98. (Previously presented) The process of claim 71, wherein the one or more Lewis acid(s) is independently selected from the group consisting of aluminum trichloride, aluminum tribromide, ethylaluminum dichloride, ethylaluminum sesquichloride, diethylaluminum chloride, methylaluminum dichloride, methylaluminum sesquichloride, dimethylaluminum chloride, boron trifluoride, and titanium tetrachloride.
- 99. (Previously presented) The process of claim 71, wherein the one or more initiator(s) comprise a hydrogen halide, a carboxylic acid, a carboxylic acid halide, a sulfonic acid, an alcohol, a phenol, a polymeric halide, a tertiary alkyl halide, a tertiary aralkyl halide, a tertiary alkyl ester, a tertiary aralkyl ester, a tertiary aralkyl ether, a tertiary aralkyl ether, an alkyl halide, an aryl halide, an alkylaryl halide or an arylalkylacid halide.
- 100. (Previously presented) The process of claim 71, wherein the one or more initiator(s) is independently selected from the group consisting of HCl, H₂O, methanol, (CH₃)₃CCl, C₆H₅C(CH₃)₂Cl, (2-Chloro-2,4,4-trimethylpentane) and 2-chloro-2-methylpropane.
- (Previously presented) The process of claim 71, wherein the one or more initiator(s) is 101. independently selected from the group consisting of hydrogen chloride, hydrogen bromide, hydrogen iodide, acetic acid, propanoic acid, butanoic acid; cinnamic acid, benzoic acid, 1-chloroacetic acid, dichloroacetic acid, trichloroacetic acid, trifluoroacetic acid, p-chlorobenzoic acid, p-fluorobenzoic acid, acetyl chloride, acetyl bromide, benzoyl benzoyl chloride, chloride, cinnamyl bromide, p-fluorobenzoylchloride, trifluoroacetylchloride, trichloroacetylchloride, methanesulfonic acid, trifluoromethanesulfonic acid, trichloromethanesulfonic acid, p-toluenesulfonic acid, methanesulfonyl chloride, methanesulfonyl bromide, trifluoromethanesulfonyl chloride, trichloromethanesulfonyl toluenesulfonyl chloride, methanol, ethanol, propanol, 2-propanol, 2-methylpropan-2ol, cyclohexanol, benzyl alcohol, phenol, 2-methylphenol, 2,6-dimethylphenol, p-2-2,3,4,5,6-pentafluorophenol, and p-fluorophenol, chlorophenol, hydroxynaphthalene.
- 102. (Previously presented) The process of claim 71, wherein the one or more initiator(s) is independently selected from the group consisting of 2-chloro-2,4,4-trimethylpentane;

> 2-bromo-2-2-chloro-2-methylpropane; 2-bromo-2,4,4-trimethylpentane; 2-bromo-2,4,4,6,6-2-chloro-2,4,4,6,6-pentamethylheptane; methylpropane; 1-chloroadamantane; 1-chloro-1-methylethylbenzene; pentamethylheptane; chloroethylbenzene; 1, 4-bis(1-chloro-1-methylethyl) benzene; 5-tert-butyl-1,3-bis(1chloro-1-methylethyl) benzene; 2-acetoxy-2,4,4-trimethylpentane; 2-benzoyloxy-2,4,4-trimethylpentane; 2-acetoxy-2-methylpropane; 2-benzoyloxy-2-methylpropane; 2-acetoxy-2,4,4,6,6-pentamethylheptane; 2-benzoyl-2,4,4,6,6-pentamethylheptane; 1acetoxy-1-methylethylbenzene; 1-aceotxyadamantane; 1-benzoyloxyethylbenzene; 5-tert-butyl-1,3-bis(1-acetoxy-1-1,4-bis(1-acetoxy-1-methylethyl) benzene; 2-isopropoxy-2,4,4-2-methoxy-2,4,4-trimethylpentane; benzene; methylethyl) trimethylpentane; 2-methoxy-2-methylpropane; 2-benzyloxy-2-methylpropane; 2methoxy-2,4,4,6,6-pentamethylheptane; 2-isopropoxy-2,4,4,6,6-pentamethylheptane; 1-methoxy-1-methylethylbenzene; 1-methoxyadamantane; 1-methoxyethylbenzene; 5-tert-butyl-1,3-bis(1-methoxy-1benzene; 1,4-bis(1-methoxy-1-methylethyl) methylethyl) benzene, and 1,3,5-tris(1-chloro-1-methylethyl) benzene.

- 103. (Previously presented) The process of claim 71, wherein the one or more initiator(s) further comprise a weakly-coordinating anion.
- 104. (Previously presented) The process of claim 71, wherein the process is substantially absent of water.
- 105. (Previously presented) The process of claim 71, wherein the one or more initiator(s) comprise greater than 30 ppm water (based upon weight).
- 106. (Previously presented) The process of claim 1, wherein the one or more monomer(s) comprises isobutylene.
- 107. (Previously presented) The process of claim 71, wherein the one or more monomer(s) comprises isobutylene and para-alkylstyrene or isoprene.
- 108. (Previously presented) The process of claim 71, wherein the reactor is independently selected from the group consisting of a continuous flow stirred tank reactor, a plug flow reactor, a moving belt or drum reactor, a jet or nozzle reactor, a tubular reactor, a batch reactor, and an autorefrigerated boiling-pool reactor.

- 109. (Previously presented) The polymerization process of claim 71, wherein the diluent has a dielectric constant greater than 10 at -85°C.
- 110. (Previously presented) The polymerization process of claim 71, wherein polymerization process forms a polymer having a diluent mass uptake of less than 4 wt%.
- 111. (Previously presented) The polymerization process of claim 71, the diluent comprising methyl chloride and one or more hydrofluorocarbon(s) independently selected from the group consisting of difluoromethane, 1,1-difluoroethane, and 1,1,1,2-tetrafluoroethane.
- 112. (Previously presented) The process of claim 111 wherein the diluent further comprises a non-reactive olefin, one or more other hydrocarbons, and/or an inert gas.
- 113. (Previously presented) The process of claim 71, wherein the diluent is independently selected from the group consisting of at least one of a hydrofluorocarbon or a blend of a hydrofluorocarbon and methyl chloride.

This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

ects in the images include but are not limited to the items checked:	
BLACK BORDERS	,
IMAGE CUT OFF AT TOP, BOTTOM OR SIDES	
FADED TEXT OR DRAWING	
BLURRED OR ILLEGIBLE TEXT OR DRAWING	
SKEWED/SLANTED IMAGES	
COLOR OR BLACK AND WHITE PHOTOGRAPHS	
GRAY SCALE DOCUMENTS	
LINES OR MARKS ON ORIGINAL DOCUMENT	
REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY	
OTHER:	

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.